

# Technical Commercial data Sheet

## BITUVER X-5

### Waterproofing bitumen polymer membrane

**BITUVER X-5** membranes are realized with elastoplastic (BPP) compound that reaches  $-5^{\circ}\text{C}$  cold flexibility made by a low filler content. The products are reinforced by polyester stabilized with glass filaments or by glass mat.

**BITUVER X-5** is also available in the "TEX" version with "DECOTEX" treatment, consisting in the application on the upper face of a special black polypropylene tissue.

**BITUVER X-5 MINERAL** is available with natural or colored slates.

#### Application

- Use Personal Protective Equipment as requested by law;
- Clean properly the surface on which membranes has to be applied;
- The treatment of the application surface with Bituver ECOPRIVER water based bituminous primer is suggested;
- **BITUVER X-5** is meant to be applied by flame with a gas propane blow torch by heating the lower face, covered with a special termofusibile film;
- Apply between  $+5^{\circ}\text{C}$  and  $+35^{\circ}\text{C}$ .

#### Suggested uses

**BITUVER X-5** membranes can be used on all type of structures as base layers, intermediate layers, earth retention and foundation. **Ideal also under heavy protection.** **BITUVER X-5 MINERAL** can be used also as top layers or under tiles. **BITUVER X-5** (when painted) could be used as top layer.

#### Storage

It is advisable to keep the rolls in warehouse, not exposed to the sun rays and at a higher temperature than  $+5^{\circ}\text{C}$ . Keep the rolls in the upright position. If possible, avoid stacking pallets, especially with slated membranes. It is advisable to use the product within 2/3 months from delivery.



TYPE	REINFORCEMENT	UPPER FACING	THICKNESS WEIGHT/m2	TYPE
BITUVER X-5 3 KG V	Glass mat	Sand	3 kg	300
BITUVER X-5 4 KG V	Glass mat	Sand	4 kg	250
BITUVER X-5 3 MM P	Polyester	Sand	3 mm	250
BITUVER X-5 4 MM P	Polyester	Sand	4 mm	230
BITUVER X-5 TEX 4 MM P	Polyester	Polypropylene TNT	4 mm	230
BITUVER X-5 MINERAL 4 KG P	Polyester	Slate	4 kg	250
BITUVER X-5 MINERAL 4,5 KG P	Polyester	Slate	4,5 kg	230

Dimensional features	Length	10 m - 1% (UNI EN 1848-1)	Toll. $\geq$
	Width	1 m - 1% (UNI EN 1848-1)	Toll. $\geq$
	Thickness	(UNI EN 1849-1)	Toll. 0,2 mm
	Weight/m2	(UNI EN 1849-1)	Toll. 10%



CODICE: STCBE 414  
 REVISIONE: 01  
 DATA: ottobre 2017  
 PAGINA: Pag. 1 di 2

Saint-Gobain PPC Italia S.p.A. – Attività Isover  
 Sede: Via Ettore Romagnoli, 6 – 20146 Milano

Servizio Clienti Bituver: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. 0871/588021 - Fax 0871/ 552483  
[www.bituver.it](http://www.bituver.it)



# Technical Commercial data Sheet

## BITUVER X-5

Test	Rif. Norma	Bituver X-5 V	Bituver X-5 P	Bituver X-5 MINERAL P	TOLERANCES
Visible Faults	UNI EN 1850-1	assenti	assenti	assenti	-
Straightness	UNI EN 1848-1	10 mm	10 mm	10 mm	≤
Water tightness	UNI EN 1928	60 kPa	60 kPa	60 kPa	≥
Cold flexibility	UNI EN 1109	- 5 °C	- 5 °C	- 5 °C	≤
L dimensional stability	UNI EN 1107-1	NPD	- 0,3 %	- 0,3 %	≥
Flow resistance	EN 1110	120 °C	120 °C	120 °C	≥
Flow resistance after ageing	UNI EN 1296 UNI EN 1110	110 °C	110 °C	110 °C	- 10 °C
Tensile strength at breaking L/T	UNI EN 12311-1	300/200 N/50 mm	400/300 N/50 mm	400/300 N/50 mm	- 20 %
Elongation at breaking L/T	UNI EN 12311-1	2/2 %	35/40 %	35/40 %	- 15 v.a (P) - 2 v.a. (V)
Shear of the joints (L/T)	UNI EN 12317-1	-	350/250 N/50 mm	-	- 20 %
Tear resistance (B method) L/T	UNI EN 12310-1	70/70 N	140/140 N	140/140 N	- 30 %
Static load resistance	UNI EN 12730	NPD	10 Kg	10 Kg	≥
Dynamic punching resistance	UNI EN 12691	NPD	700 mm	700 mm	≥
Vapour permeability	UNI EN 1931	μ 20000	μ 20000	μ 20000	-
UV ageing	UNI EN 1297	-	Supera la prova (4 mm)	-	-
Fire reaction	EN 13501-1	NPD	NPD	NPD	-
External fire reaction	EN 13501-5	F roof	F roof	F roof	-
Granules adhesion	UNI EN 12039	-	-	30%	≤
Water tightness after exposure to chemical agents artificial ageing	UNI EN 1928 UNI EN 1847/ UNI EN 1296	NPD	NPD	-	-
Resistance to water penetration	UNI EN 1928	-	-	CLASSE W1	-
Res. to water penetration Tensile properties after artificial ageing	App. C EN 13859-1	-	-	NPD	-
Uses	EN 13707 Sistema 2+	Base layer Middle layer	Base layer Middle layer Top layer (*) Under Heavy layer	Top layer	-
	EN 13969 Sistema 2+	Foundation Earth retention	Foundation Earth retention	-	-
	EN 13859-1 Sistema 4	-	-	Under tiles	-

(\*) 4mm with protective paint.

The Saint-Gobain PPC Italia S.p.A. quality system is certified according to EN ISO 9001. Follow proper application and storage modalities. The CE marking of this bituminous membrane is in accordance with the European Construction Products Regulation 305/2011, is in agreement to the reference technical standards and is supported by certification no. 1370-CPR-0050. Saint Gobain PPC Italia has the right to change the technical data of this data sheet any time with no need of notice



CODICE: STCBE 414  
REVISIONE: 01  
DATA: ottobre 2017  
PAGINA: Pag. 2 di 2

Saint-Gobain PPC Italia S.p.A. – Attività Isover  
Sede: Via Ettore Romagnoli, 6 – 20146 Milano

Servizio Clienti Bituver: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. 0871/588021 - Fax 0871/ 552483  
www.bituver.it

